



Asian Institute of Technology

Asian Center for Soil Improvement and Geosynthetics (ACSIG)
School of Engineering and Technology (SET)

Postal Address:
P.O. Box 4
Klong Luang,
Pathumthani 12120
Thailand

Street Address:
Km. 42 Phaholyothin Highway
Klong Luang
Pathum Thani 12120
Thailand

Tel: (66-2)524-5501
Tel: (66-2)524-5505
e-mail: acsiglab@gmail.com
<http://www.ait.ac.th>

LABORATORY TEST ON GALVANIZED WIRE

Submitted to: YORN WIRE STEEL KH
Sample Description: Hot-dipped Galvanized Wire 2.4mm and 3.4mm
Date Tested: 8 May 2024
Date Submitted: 8 May 2024
Testing Atmosphere: $23 \pm 2^{\circ}\text{C}$ temperature and $65 \pm 5\%$ humidity
Job No: GST24-105

Zinc or Zinc-alloy Coatings Test (ASTM A90)

Test Results:

Sample Description	Measured value g/m^2
Hot-dipped Galvanized Wire 2.4mm	375.15
Hot-dipped Galvanized Wire 3.4mm	339.83

Submitted by:

Ms. Nussarin Sudrohman
Manager, ACSIG
Asian Institute of Technology

Dr. Kuo-Chieh Chao
Director, ACSIG
Asian Institute of Technology

ASIAN INSTITUTE OF TECHNOLOGY
Geotechnical and Earth Resources Engineering Program

Zinc or Zinc-alloy Coatings Test
ASTM A90

Submitted to: YORN WIRE STEEL KH

Date: 8-May-24

Sample: Hot-dipped Galvanized Wire 2.4mm and 3.4mm

Tested by: Chalermwut

Checked by: Nussarin

Zinc coating	Zinc coat, g/m ²
Hot-dipped Galvanized Wire 2.4mm	375.15
Hot-dipped Galvanized Wire 3.4mm	339.83

